



Hysol® EA 9695

Epoxy Film Adhesive

Henkel Corporation
Aerospace Group
2850 Willow Pass Road
P.O. Box 312
Bay Point, CA 94565 USA
925.458.8000
Fax: 925.458.8030
www.aerospace.henkel.com

Description

Hysol EA 9695 is a composite bonding film adhesive with excellent environmental resistance. It is suited for bonding composite structures, both for co-cure and pre-cured laminates. Its ability to cure at lower temperatures makes it suitable for repair of composite structures. Its low flow characteristics minimize prepreg resin intermingling.

Features

X-ray Opaque
Excellent Environmental Resistance
Reticulatable
Good Pre and Post Bond Moisture Resistance
Low Flow
Allows 250°F/121°C or 350°F/177°C Cure
Co-Cure with Composites
Long Outtime Facilitates Shop Floor Usage and Repair Applications

Handling

This product is in film form and is ready to use as received. The adhesive should be removed from cold storage and allowed to warm to room temperature (77°F/25°C). All moisture should be removed from the protective packaging before opening. The adhesive film has a protective liner(s) on it which must be removed prior to parts assembly (see "Applying" below). The liner(s) will always be a contrasting color from the adhesive to allow the user easy confirmation of removal.

Application

Storage Life - This product requires refrigerated storage. Store @ 0°F/-18°C or below for maximum storage life. Warranty life @ 0°F/-18°C is greater than 6 months from date of shipment. Store only in sealed containers to prevent moisture contamination. Allow all moisture to evaporate from container before opening for use.

Applying - Bonding surfaces should be clean, dry and properly prepared. For optimum surface preparation consult the Hysol Surface Preparation Guide. The adhesive film, with one liner left on it, may be tacked to the detail part for cutting to shape and size. The liner should remain with the adhesive until just before assembly of the detail to the other faying surface. This will minimize contamination of the adhesive bond. The bonded parts should be held in contact until the adhesive has cured. Usually 25 to 50 psi /17 to 34 kPa is sufficient to assure proper part mating.

Open Assembly Time - This adhesive may be used within the following schedule after removing from cold storage:

- @ 77°F/25°C at least 90 days
- @ 90°F/32°C at least 45 days

Curing - This product may be cured for 1 - 1 ½ hours @ 250°F/121°C or for 1 - 2 hours @ 350°F/177°C. Heat up rate to the cure temperature is not critical, but should be between 1° and 10°F (0.6° and 5.6°C) per minute. Pressure should be applied before heating the parts to be bonded and maintained until cool down of the assembly.

Cleanup - It is important to remove excess adhesive from the part and bonding tools before it hardens. Once the adhesive is cured, it is difficult to remove except by mechanical abrasion. Uncured adhesive may be removed with denatured alcohol and many common industrial solvents. Be careful to prevent any solvent from entering the uncured bondline as solvent will degrade the final bond performance. Consult with your supplier's information pertaining to the safe and proper use of solvents.

Bond Strength Performance

Tensile Lap Shear Strength

Tensile lap shear strength tested per ASTM D1002. Adherends are 2024-T3 bare aluminum treated with phosphoric acid anodizing per ASTM D3933. Adhesive cure cycle: 120 minutes @ 350°F/177°C.

Typical Results for Film Weight

| <u>Test Temperature, °F/°C</u> | 0.035 psf (171 g/m²) | | 0.050 psf (244 g/m²) | |
|--------------------------------|--|------------|--|------------|
| | psi | MPa | psi | MPa |
| 77/25 | 4,600 | 31.7 | 5,000 | 34.5 |
| 250/121 | 4,400 | 30.3 | -- | -- |
| 300/149 | 2,900 | 20.0 | 3,400 | 23.4 |

Double Lap Shear Strength

Properties were measured on double overlap shear specimens of pre-cured epoxy graphite laminate. Adhesive cure cycle: 120 minutes @ 350°F/177°C.

Typical Results for Film Weight

| <u>Test Temperature, °F/°C</u> | 0.035 psf (171 g/m²) | | 0.050 psf (244 g/m²) | |
|--------------------------------|--|------------|--|------------|
| | psi | MPa | psi | MPa |
| -67/-55 | 4,500 | 31.0 | 4,400 | 30.3 |
| 77/25 | 5,000 | 34.5 | 5,000 | 34.5 |
| 160/71 | 5,000 | 34.5 | 5,400 | 37.2 |
| 270/132 | 2,700 | 18.6 | 2,800 | 19.3 |

Flatwise Tensile

Composite to Honeycomb (co-cured). Specimen was 2" x 2" (5.1 cm x 5.1 cm) honeycomb sandwich bonds using two plies of co-cured epoxy graphite prepreg face sheets bonded to honeycomb core (HRP ³/₁₆ inch/4.76 mm cell, ½ inch/12.7 mm thick - 8 pcf/128 Kg/m³).

Typical Results for Film Weight

| <u>Test Temperature, °F/°C</u> | 0.035 psf (171 g/m²) | | 0.050 psf (244 g/m²) | |
|--------------------------------|--|------------|--|------------|
| | psi | MPa | psi | MPa |
| -67/-55 | 1,000 | 6.9 | 1,000 | 6.9 |
| 77/25 | 1,000 | 6.9 | 1,200 | 8.3 |
| 160/71 | 1,000 | 6.9 | 1,200 | 8.3 |

Short Beam Shear Performance

Composite to Honeycomb (co-cured). Properties were obtained using 3" x 6" (7.1 cm x 15.2 cm) honeycomb sandwich bonds from a three-ply co-cured epoxy graphite prepreg face sheet bonded to honeycomb core (HRP ³/₁₆ inch/4.46 mm cell, ½ inch/12.7 mm thick - 8 pcf/128 kg/m³). Pull rate used 4" (10.2 cm) per minute. Adhesive cure cycle: 120 minutes @ 350°F/177°C.

Typical Results for Film Weight
0.050 psf (244 g/m²)

| <u>Test Temperature, °F/°C</u> | <u>psi</u> | <u>MPa</u> |
|--------------------------------|------------|------------|
| -67/-55 | 750 | 5.2 |
| 77/25 | 650 | 4.5 |
| 160/71 | 650 | 4.5 |

Peel Performance

Bell peel strength tested on 2024T-3 bare aluminum adherends treated with phosphoric acid anodizing per ASTM D3933. Cure cycle: 120 minutes @ 350°F/177°C.

| <u>Test Temperature, °F/°C</u> | <u>Lb/in</u> | <u>N/25mm</u> |
|--------------------------------|--------------|---------------|
| 77/25 | 20 | 89.6 |

Environmental Conditioning

Composite Double Lap Shear Strength
 Cure cycle: 120 minutes @ 350°F/177°C

| | Typical Results 0.050 psf (244 g/m²) | |
|-----------------------------|--|------------|
| | <u>psi</u> | <u>MPa</u> |
| Tested @ 77°F/25°C | | |
| Dry | 5,400 | 37.2 |
| 1000 hour soak @ 160°F/71°C | 4,400 | 30.3 |
| Tested @ 160°F/71°C | | |
| Dry | 5,400 | 37.2 |
| 1000 hour soak @ 160°F/71°C | 3,900 | 26.9 |

Composite Flatwise Tensile Performance

| | Typical Results 0.050 psf (244 g/m²) | |
|--------------------------|--|------------|
| | <u>psi</u> | <u>MPa</u> |
| Tested @ 160°F/71°C | | |
| Dry | 1,200 | 8.3 |
| 10 day soak @ 160°F/71°C | 850 | 5.9 |

Environmental conditioning was 160°F/71°C, 100% RH.

Composite specimens for flatwise tensile were co-cured using a 120 minute cure @ 350°F/177°C with a heat up rate of 3° to 5°F(1.8° to 3°C) per minute. Autoclave pressure was 45 psi/310 kPa during cure cycle. Pre-cured laminates for double overlap shear used the same cure with the exception of 85 psi/585 kPa pressure.

Service Temperature

Service temperature is defined as that temperature at which this adhesive still retains 1000 psi/6.9 MPa using test method ASTM D1002 and is >300°F/149°C.

Bulk Resin Properties

T_g dry - cured 1 hr. @ 250°F/121°C 252°F/122°C
T_g dry - cured 1 hr. @ 350°F/177°C 302°F/150°C
T_g, measured by dynamic mechanical analysis, is taken at the knee of the G' curve.

Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood.
For industrial use only.

General:

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty containers retain product residue and vapors so obey all precautions when handling empty containers.

ONE PART

CAUTION! This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

Hysol® is a registered trademark of Henkel Corporation.

Rev. 1/01

DISCLAIMER: The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the materials are responsible for assuring that it is suitable for their needs, environmental and use. All data is subject to change as Henkel deems appropriate.

Users should review the Materials Safety Data Sheet (MSDS) and product label for the material to determine possible health hazards, appropriate engineering controls and precautions to be observed in using the material. Copies of the MSDS and label are available upon request.

