



TURCO[®] 4338-L

HOT SECTION JET ENGINE CLEANING COMPOUND

DESCRIPTION:

TURCO 4338-L is a 2-part liquid alkaline permanganate formulation developed specifically for jet engine cleaning. TURCO 4338-L modifies high temperature heat scale by chemically changing the structure of the oxide deposit to one that is properly conditioned for ease of chemical removal in subsequent processing steps.

FEATURES:

TURCO 4338-L offers these features:

1. Approved by Rolls-Royce, GEAE, and Pratt & Whitney
2. Supplied as two liquid concentrates that are mixed together with water for use
3. Liquid concentrate form provides much greater safety and ease of handling compared to dry powdered products, both for tank make-up and for tank maintenance
4. May be used over a wide range of concentrations to handle various types of scale
5. TURCO 4338-L is used on all ferrous and high temperature alloys
6. TURCO 4338-L meets the corrosion requirements of MIL-D-26549, Amend. 2
7. Used in mild steel tanks

NOTE: TURCO 4338-L should not be used on reactive alloys such as aluminum.

HOW TO USE TURCO 4338-L:

A. Prepare a solution of TURCO 4338-L in a mild steel tank by first adding enough water to comprise about 40% of the final volume. While mixing, add sufficient TURCO 4338-L Part 1 and TURCO 4338-L Part 2 for each individually to comprise 15 to 25% by volume of the final solution. TURCO 4338-L Parts 1 and 2 should be used in equal volumes. TURCO 4338-L Part 1 should be added to the water first, while mixing. The appropriate amount of TURCO 4338-L Part 2 should then be added to that solution, while continuing to mix. Heat to 90°C while mixing. Add sufficient good quality water to make up the final volume while mixing.

Step 1. Immerse parts in Turco 4181-L at 50-75% by volume at 80° to 95°C for 30 to 60 minutes.

Step 2. Thorough water overflow dip rinse.

Step 3. Immerse parts in TURCO 4338-L solution at 80° to 95°C for 30 to 60 minutes.

Step 4. Thorough water overflow dip rinse.

Step 5. Immerse in Scale Gon #5 at 20-30% by volume at 80°to 90°C for 30-60 minutes.

Step 6. Water dip rinse. Follow with pressure rinse with air/water hand rinse gun to blast off the loosened scale deposit and reveal the shiny base metal surface.



Step 7. Final clean in 4181-L at 50-75% at 80° to 95°C.

Step 8. Thorough water overflow dip rinse.

CONTROL:

A laboratory test procedure is available upon request.

DISPOSAL INFORMATION:

Dispose of sludge and/or spent solution per local, state and regional regulations. Refer to your TURCO MATERIAL SAFETY DATA SHEET for additional information.

DANGER! Contact may cause severe burns to skin and eyes.

The TURCO 4338-L solution contains sodium hydroxide and permanganate. Avoid contact with eyes, skin and clothing. Do not take internally. Use with adequate (equivalent to outdoor) ventilation.

TURCO 4338-L is a strongly alkaline, highly oxidizing solution which will produce burns on contact with skin. Protective clothing, such as a chemical face shield or goggles, gloves, boots and apron, made of alkali resistant materials should be worn when using and handling this product.

Hazardous carbon monoxide gas can be formed upon contact with food and beverage products in enclosed spaces and can be fatal. Follow appropriate tank entry procedure. (See ANSI-Z117.1-1977.)

Store and transport in closed containers away from organic materials, such as paints, lubricants, paper and wood products, at a temperature below 55°C.

Before using this product refer to container label and TURCO MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.

NOTICE:

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience with this or similar products. However, since conditions of actual use are beyond our control, any recommendations or suggestions are made without warranty, express or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage or injury, direct or consequential, arising out of the use of this product.

Rev. 8/99 (Sup. 3/98)
TDB #185