



## Technical Information Bulletin

---

### TURCO® 5065

#### THIXOTROPIC STRIPPER FOR EPOXIES & DIFFICULT TO REMOVE ORGANIC COATINGS

#### DESCRIPTION

CAUTION: TURCO 5065 is an especially effective acid activated material specifically developed for stripping epoxies and other difficult to remove organic coatings. Its heavy-duty character is dependent upon inclusion of certain constituents having recognized toxicity and hazard characteristics. Your attention is directed to the toxicity and hazard information in the MSDS and on our labels.

#### PROPERTIES

*Appearance:* Varies from yellow to bright red.

*Corrosion:* Test panels, completely immersed in the TURCO 5065 for seven (7) days at 32°C, changed weight as follows:

1100 Aluminum: -0.42 milligrams per sq. cm.

1020 Steel: -0.29 milligrams per sq. cm.

TURCO 5065 is not recommended for use on magnesium or high strength steels.

*Flammability:* TURCO 5065 is non-flammable.

#### USE INSTRUCTIONS

*Storage:* Must be stored in a protected area out of direct sunlight, preferably at such temperatures that contents are not less than 0°C. and not in excess of 32°C. Avoid freezing and heating of containers.

*Equipment:* Barrel Pump or similar non-atomizing spray equipment. May also be applied by brush. Face shields or goggles, and protective solvent and acid resistant gloves, boots and clothing are recommended for using personnel.

*Concentration:* Apply TURCO 5065 full strength, as received.

*Stripping:* Allow TURCO 5065 sufficient dwell time for thorough loosening of the paint. When paint is loose, thoroughly agitate all areas with a stiff bristle brush.

*Rinsing:* TURCO 5065 and paint residues may be rinsed with high pressure, high volume cold water, or with a steam cleaning machine. Slight brushing during the rinse operation insures complete removal of all residues.

#### TOXICITY AND HAZARDS

Consult MSDS before use.

*NOTICE:*

*The above information and recommendations are based upon our laboratory tests and field use experience with these and similar products. However, since conditions of actual use are beyond our control, any recommendations are made without warranty, express or implied. Manufacturers and sellers sole obligation shall be to replace those portions of any products shown to be defective. Neither shall be liable for any loss, damage or injury, direct or consequential, arising from the use of these products.*